

Solfir Specification :

- 240mm with beaded cuff
- Powder Free
- Ambidextrous



Antistatic Approved

AQL 1.5

Highly Comfortable

EN Certified

Food Content Tested

Inspection Criteria

Sampling & Inspection ISO 2859

	Inspection Level	AQL
Watertight Test	G1	1.5
Major Defects	G1	2.5
Minor Defects	G1	4.0
Dimensions	S2	4.0
Physical Properties	S2	4.0

Dimensions (Available in 5 sizes)

Size	Glove Weight (g)	Palm Width (mm)		Length (mm)	
		ASTM D6319	SOLFIR	ASTM D6319	SOLFIR
XS	4.6 ± 0.2	70 ± 10	70 - 79	Min. 220	Min. 240
S	5.0 ± 0.2	80 ± 10	80 - 89	Min. 220	Min. 240
M	5.4 ± 0.2	95 ± 10	90 - 99	Min. 230	Min. 240
L	5.8 ± 0.2	110 ± 10	100 - 109	Min. 230	Min. 240
XL	6.2 ± 0.2	120 ± 10	110 - 119	Min. 230	Min. 240

Thickness :

Location of Thickness Measurement	Single Wall (mm)	
	ASTM D6319	SOLFIR
Finger	Min 0.05	Min 0.13
Palm	Min 0.05	Min 0.10
Cuff	N/A	Min 0.08

Physical Properties :

	Before Aging		After Aging	
	ASTM D6319	SOLFIR	ASTM D6319	SOLFIR
Tensile Strength (MPa)	Min. 14	Min. 14	Min. 14	Min. 14
Elongation (%)	Min. 500	Min. 500	Min. 400	Min. 400
Force at Break (N)	N/A	Min. 9	N/A	Min. 6